

# **SALOMON'S METALEN B.V.**

## **CoNiFer**

CoNiFer is a non-magnetic Cobalt-Chromium-Nickel-Molybdenum alloy having a unique combination of very high strength, excellent corrosion resistance and high fatigue strength. CoNiFer is highly resistant to sulfide stress corrosion cracking and as a result is the alloy of choice in the most demanding sour well environments.

In seawater CoNiFer is virtually immune to crevice and stress corrosion and pitting even at the highest strength levels and can operate at cryogenic temperatures up to 454°C.

Applications include springs, torsion bars, seals, medical devices & implants and orthodontic wire.

Industries supplied include: Oil & Gas Extraction, Medical & Dental, Aerospace, Defense and Space Exploration.

### **Nominal Composition**

	Co	Cr	Ni	Mo	Mn	Fe	Si	C	Be	P	S
min	39	19	14	6	1.5						
max	41	21	16	8	2.5	balance	1.2	0.15	0.1	0.015	0.015

### **Physical Properties**

	At 20°C
Density	8.30 g/cm <sup>3</sup>
Modulus of Elasticity (E)	190 GPa
Modulus of Rigidity (G)	77.2 GPa
Coefficient of Expansion	15.2 x μm/m-°C (20-300°C)
Electrical Resistivity	99.6 μ ohm.cm
Thermal Conductivity	12.5 W/m-K

### **Applicable Specifications**

Wire & Bar	AMS 5833, AMS 5834, ASTM F1058, NACE MR0175 (ISO 15156-3), ISO 5832-7.
------------	--

### **Typical Mechanical Properties – Spring Applications**

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	1120°C	830-1035 MPa	-184°C to 454°C
Spring Temper		1515-2000 MPa	-184°C to 454°C
Spring Temper + Aged	After spring coiling. Age: 527°C for 5 hours.	1790-2275 MPa	-184°C to 454°C

#### **Limitation of Liability**

The information contained in this datasheet is not an exhaustive statement of all relevant information. It is a general guide for customers to the products and services available from Salomon's Metalen B.V. and no representation is made or warranty given in relation to this document or the products or processes it describes.